

检测报告

Test Report

报告编号 Report No.	WP-17083259-JC-01EnR1
样品名称 Sample Name	adjustable plastic pedestals
样品来源 Sample Origin	Commission test
委托单位 Client	Hangzhou Moonbay Industrial Co., Ltd.




Test Report

Report No.: WP-17083259-JC-01EnR1


Page No.: 1 / 3

Name of Sample	adjustable plastic pedestals	Specification and Type	/
Description of Sample	Particle & Sheet		
Client	Hangzhou Moonbay Industrial Co., Ltd.		
Client Address	703 Building 2, Zhongdong International Plaza, Fengqing Avenue, Xiaoshan, Hangzhou, China		
Sampling Date	2017-08-28	Completion Date	2017-09-07
Test Item(s)	Tensile strength; Flexural strength; Flexural modulus		
Reference Standard(s)	ASTM D 638-2014 < Standard Test Method for Tensile Properties of Plastics> ASTM D 790-2017 <Standard Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials>		
Test Result (s)	Please refer to next page (s)		
Note(s)	/		

Compiled by:



Inspected by:



Approved by:



Issued Date:

2017-09-07

Test Report

Report No.: WP-17083259-JC-01EnR1

Page No.: 2 / 3

1. Test Results:

Sample No.	Sample Name	Test Item(s)	Test Result(s)	Unit(s)	Reference Standard(s)
201708280138	adjustable plastic pedestals	Tensile strength	31.21	MPa	ASTM D 638-2014
		Flexural strength	33.52	MPa	ASTM D 790-2017
		Flexural modulus	1376.23	MPa	
The following is blank					

Note:

1. Tensile strength use the standard specimens injection of the particle provided by the client; The flexural strength and flexural modulus use the specimens provided by the client.

*** End of the Page ***

Test Report

Report No.: WP-17083259-JC-01EnR1

Page No.: 3 / 3

2. Sample Picture(s):



*** End of the Report ***

DECLARE:

1. The report (including copy) is void either without the stamp of Micro-spectrum Technology or without the signature of the Inspector and approver.
2. The report is void with any alteration, addition, and deletion.
3. The copy report is void without the stamp of Micro-spectrum Technology.
4. Any disagreement on the report should be raised to Shanghai Micro-spectrum Chemical Technology Service Co., Ltd. within 15 working days since the report is delivered.
5. The above some service items or test methods might be non-standard methods. The report results do not have a notarized role. The results presented in this report are based on the sample(s) tested.
6. The consigner is responsible to the reality of the testing samples and information related.